

#### **Technical Datasheet**

Create Date: 16 11 2017 - Seite 1/

# **Stainless Steel Spray**



#### corrosion-resistant and effective surface coating

WEICON Stainless Steel Spray is a chemical, corrosion, and weather resistant surface coating on the basis of acrylic resin and stainless steel pigments. It is temperature resistant up to +300°C (+572°F) for short periods of time.

Stainless Steel Spray can be used wherever a resistant and effective protective layer is required. The alloy is comprised of e.g. chromium, nickel and manganese.

WEICON Stainless Steel Spray can be used to repair damaged stainless steel parts on truck bodies, silos and pipelines, and outdoor applications. It can also be used for decorative purposes and for the optical refinement of glass, wood, stone, ceramics and most plastics.

# **Technical Data**

Colour	RAL 9007*, stainless steel metallic, matt
Application	indoors and outdoors
Binding agent	acrylic resin
Pigment	stainless steel pigments
Pigment purity	stainless steel alloy approx. 98,5 %
Percentage of metal in dry film	45 %
Specific weight	0,9 - 1,0 g/cm <sup>3</sup>
Recommended primer	Zinc-Spray
Processing temperature	+5 to +35, optimal +18 to +35 °C
Consumption at 1.5 cross coats	120 ml/m²
Layer thickness at 1.5 cross coats	20 -30 μm
Dust dry after	10 min.

Hardened after	4,6 h
Overpaintable after	4-6 h
Abrasion-resistant yes/no	abrasion-resistant
Cross cutting DIN 53151/ ISO 2409	cross cut characteristic value GT 0 to GT 1
Mandrel bend test DIN EN ISO 1519	no hair cracking
Top coating	not required
Storage stability	24 months
Temperature resistance	-50 to +300 °C
ISSA-Code	53.402.43
IMPA-Code	45 08 13

<sup>\*</sup>corresponds approximately to the specified RAL colours

#### Surface pre-treatment

Clean and degrease surfaces with WEICON Surface Cleaner.

#### **Processing**

Clean and degrease surfaces with Cleaner S. Shake can before use till the mixing ball can be heard. Spray on evenly and crosswise at room temperature (approx.  $+20^{\circ}\text{C}$  /  $+68^{\circ}\text{F}$ ) and at about 25 cm distance from surface. Dust-dry after approx. 10 minutes, fully hardened after approx. 4-6 hours.

#### Storage

Pressurized container: protect from sunlight and do not expose to temperatures exceeding +50°C.

### Safety and health

When using WEICON products, the physical, safety technical, toxicological and ecological data and regulations in our EC safety data sheets (www.weicon.com) must be observed.

## Available sizes:

11100400 Stainless Steel Spray 400 ml

Accessories:

11207400 Surface Cleaner, 400 ml 11850200 Hand Protective Foam, 200 ml

#### Note

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

WEICON GmbH & Co. KG (Headquarters) Germany phone +49 (0) 251 9322 0 info@weicon de

WEICON SA (Pty) Ltd South Africa phone +27 (0) 21 709 0088 info@weicon.co.za WEICON Middle East L.L.C. United Arab Emirates phone +971 4 880 25 05 info@weicon ae

WEICON South East Asia Pte Ltd Singapore phone (+65) 6710 7671 info@weicon.com.sg WEICON Inc.
Canada
phone +1 877 620 8889
info@weicon.ca

WEICON Czech Republic s.r.o. Czech Republic phone +42 (0) 417 533 013 WEICON Kimya Sanayi Tic. Ltd. Şti. Turkey phone +90 (0) 212 465 33 65 info@weicon.com.tr

WEICON Ibérica S.L. Spain phone +34 (0) 914 7997 34 info@weicon es WEICON Romania SRL Romania phone +40 (0) 3 65 730 763 office@weicon.com