

Mould Release Agent Liquid F 1000



Safety and health

When using WEICON products, the physical, safety technical, toxicological and ecological data and regulations in our EC safety data sheets (www.weicon.com) must be observed.

Available sizes:

10604000 Mould Release Agent Liquid F 1000 1 L
10604025 Mould Release Agent Liquid F 1000 250 ml

Accessories:

11207400 Surface Cleaner, 400 ml
13955050 Primer Applicator,

solvent-containing

Liquid F 1000 is a release agent on a waxy basis for epoxy resins and polyurethanes. It is especially suitable for release processes from smooth and non-absorbing surfaces.

Technical Data

Composition	Wax, solvent-containing
Consistency	liquid
Density at +20°C (+68°F)	0,71 g/cm ³
Consumption	50 to 100 ml/m ²
Processing temperatur	+15 to +25 °C
Application temperature	to +70 °C
Colour	with, milky
IMPA-Code	81 29 59/60

Surface pre-treatment

The surface to be treated must be clean, dry and free of grease (e.g. cleaning and degreasing with WEICON Surface Cleaner).

Processing

Apply sufficient Mould Release Agent Liquid F 1000 with a fibre-free pulp cloth, with a lint-free paper cloth or with a paint-brush on the surface and let it dry. When using new moulds repeat the process two to three times. After application let the Mould Release Agent evaporate for approx. 10 minutes until the surface is mat, dry and tack-free. Do not apply Mould Release Agent on absorbing or porous surfaces (if necessary use Mould Release Agent Wax P 500).

Note

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

WEICON GmbH & Co. KG
(Headquarters)
Germany
phone +49 (0) 251 9322 0
info@weicon.de

WEICON Middle East L.L.C.
United Arab Emirates
phone +971 4 880 25 05
info@weicon.ae

WEICON Inc.
Canada
phone +1 877 620 8889
info@weicon.ca
www.weicon.ca

WEICON Kimya Sanayi Tic. Ltd. Şti.
Turkey
phone +90 (0) 212 465 33 65
info@weicon.com.tr
www.weicon.com.tr

WEICON Romania SRL
Romania
phone +40 (0) 3 65 730 763
office@weicon.com

WEICON SA (Pty) Ltd
South Africa
phone +27 (0) 21 709 0088
info@weicon.co.za

WEICON South East Asia Pte Ltd
Singapore
phone (+65) 6710 7671
info@weicon.com.sg

WEICON Czech Republic s.r.o.
Czech Republic
phone +42 (0) 417 533 013
info@weiconcz.cz

WEICON Ibérica S.L.
Spain
phone +34 (0) 914 7997 34
info@weicon.es