

WEICONLOCK® AN 305-42 Hydraulic and Pneumatic Sealing



medium viscosity medium strength disassembly with normal tools

Hydraulic and pneumatic sealing, DVGW certificated, marking-free



Technical Data

Colour	brown
For threaded joints up to	M 20 R ¾"
Viscosity at 25°C (+77°F) according to Brookfield	500 nt mPa⋅s
Max. Gap Bridging	0,15 mm
Breakaway strength (Thread)	12 - 15 Nm
Prevailing stregth	18 - 22 Nm
Shear strength Nmm² (DIN 54452)	8 - 12 N/mm²
Handling strength at room temperature	10 - 20 min.
Final strength (100%) after	2 - 4 h
Temperature resistance	-60 to +150 °C
ISSA-Code	75.628.10/11/12
IMPA-Code	812918/19/20

^{*}Strength values based on M 10 screws, 8.8 grade, thickness of nut 0,8.d Static shear strength based on cylindrical parts of abt. Ø 13 mm, tolerance (D-d) = 0.05 mm, I/d = 0.88

Surface pre-treatment

In general, WEICONLOCK does not require special pre-treatment as slightly oily surfaces (e.g. on as received parts) will be tolerated. However, best results will be achieved on cleaned, degreased parts (use WEICON Surface Cleaner). If required, the parts should be slightly roughened.

Processing

WEICONLOCK is ready for use and should be applied evenly direct from the bottle/tube with the dispensing tip (avoid direct contact of dispensing tip with metal). Apply WEICONLOCK in circular motions on the thread. Screw pipe threads together and tighten until desired orientation. When using as flange sealing apply a continuous bead on one side. Join and tighten parts quickly. Do not pour back into the bottle any WEICONLOCK fluid which had contact with metal; even smallest metal particles will cause the content of the bottle to cure. In series construction, the use of manual or automatic applicators is recommended.

Storage

WEICONLOCK can be stored in the unopened original container for at least 24 months at room temperature. Keep away from heat sources and direct sunlight. The air in the bottle/tube keeps WEICONLOCK liquid.

Safety and health

When using WEICON products, the physical, safety technical, toxicological and ecological data and regulations in our EC safety data sheets (www.weicon.com) must be observed.

Available sizes:

30542020 WEICONLOCK® AN 305-42 Hydraulic and

Pneumatic Sealing 20 ml

30542150 WEICONLOCK® AN 305-42 Hydraulic and

Pneumatic Sealing 50 ml

30542200 WEICONLOCK® AN 305-42 Hydraulic and

Pneumatic Sealing 200 ml

Accessories:

30700200 Activator F, 200 ml 30955172 Dosing Tips, Size 1

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

WEICON GmbH & Co. KG Germany phone +49 (0) 251 9322 0 info@weicon.de www.weicon.de

WEICON SA (Pty) Ltd South Africa phone +27 (0) 21 709 0088 www.weicon.co.za

WEICON Middle East L.L.C. United Arab Emirates phone +971 4 880 25 05 info@weicon.ae www.weicon.ae

WEICON South East Asia Pte Ltd Singapore phone (+65) 6710 7671 www.weicon.com.sg

Canada phone +1 877 620 8889 www.weicon.ca

WEICON Czech Republic s.r.o. Czech Republic phone +42 (0) 417 533 013

WEICON Kimya Sanayi Tic. Ltd. Şti. Turkey phone +90 (0) 212 465 33 65 www.weicon.com.tr

WEICON Ibérica S.L. Spain phone +34 (0) 914 7997 34 www.weicon.es

WEICON Romania SRL Romania phone +40 (0) 3 65 730 763 www.weicon.com.ro

WEICON Italia S.r.I. phone (+39) 0102924871 www.weicon.it