

WEICON B Epoxy Resin



viscous steel-filled

WEICON B is particularly suited for detailed reproductions in model and mould making, for the production of tools, templates, gauges and fixtures, for filling in blowholes and microporosities, in castings and for general repair work where a casting compound is advantageous.

WEICON B can be used in machine construction, tool construction, model and mould making, and in many other applications.



Technical Data

Composition	Epoxy resin steel-filled
Specific Properties	viscous
Colour after curing	dark-grey
Mixing ratio by weight resin/hardener	100:7
Density of the mixture (200g preparation)	2.75 g/cm ³
Viscosity of the mixture	200.000 mPa·s
Consumption at a coating thickness of 1,0 mm	2,75 kg/m ²
Maximum layer thickness for each working step	10 mm
Pot life at +20°C (+68°F) 200g preparation	60 min.
Curing time mechanical loads	16 h
Final strength after	24 h
Mean strength at +25°C (+77°F) acc. to DIN 53281-83 ASTM D 1002:	

Note

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

Pressure	110 Mpa
Bending	52 Mpa
E-Modul	3.500 - 5.000 Mpa
Shore D (ATSM D 1706)	90
Shrinkage	0.03 %
Thermoforming resistance	65 °C
Temperature resistance	-35 to +120 °C
ISSA-Code	75.509.03/04
IMPA-Code	81 28 05/06

Information about surface pre-treatment and processing can be found in the manual.

Storage

Store WEICON Plastic Metal at room temperature (but up to max. +25°C) in a dry place. Unopened containers can be stored for 18 months at temperatures from +18 to +25°C (Epoxy Resin Putty max. 3 years). Opened containers should be used within 6 months.

Safety and health

When using WEICON products, the physical, safety technical, toxicological and ecological data and regulations in our EC safety data sheets (www.weicon.com) must be observed.

Available sizes:

10050005	WEICON B Epoxy Resin 0.5 kg
10050020	WEICON B Epoxy Resin 2.0 kg

Accessories:

10604025	Mould Release Agent Liquid F 1000, 250 ml
10604515	Mould Release Agent Wax P 500, 150 g
10850005	Glass Fibre Cloth Tape, 50 mm
10953001	Processing Spatula, short
10953003	Processing Spatula, long
10953010	Stirrer Stainless Steel,
11202400	Sealant and Adhesive Remover, 400 ml
11207400	Surface Cleaner, 400 ml
11450400	Mould Release Agent, 400 ml
11850200	Hand Protective Foam, 200 ml

WEICON GmbH & Co. KG
(Headquarters)
Germany
phone +49 (0) 251 9322 0
info@weicon.de

WEICON Middle East L.L.C.
United Arab Emirates
phone +971 4 880 25 05
info@weicon.ae

WEICON Inc.
Canada
phone +1 877 620 8889
info@weicon.ca
www.weicon.ca

WEICON Kimya Sanayi Tic. Ltd. Şti.
Turkey
phone +90 (0) 212 465 33 65
info@weicon.com.tr
www.weicon.com.tr

WEICON Romania SRL
Romania
phone +40 (0) 3 65 730 763
office@weicon.com

WEICON SA (Pty) Ltd
South Africa
phone +27 (0) 21 709 0088
info@weicon.co.za

WEICON South East Asia Pte Ltd
Singapore
phone (+65) 6710 7671
info@weicon.com.sg

WEICON Czech Republic s.r.o.
Czech Republic
phone +42 (0) 417 533 013
info@weiconcz.cz

WEICON Ibérica S.L.
Spain
phone +34 (0) 914 7997 34
info@weicon.es