Epoxy Resin Putty



The kneadable universal repair compound

WEICON Epoxy Resin Putty is pasty (kneadable), mineral-filled, and temperature-resistant up to +200°C. It is processed with a mixing ratio of 1:1 and is machinable and overpaintable after curing.

The Putty adheres to metal, wood, glass, rubber, ceramics, concrete and most plastics. It is resistant to petrol, oil, ester, saltwater and most acids and lyes.

WEICON Epoxy Resin Putty is suited for the sealing of pipelines and tanks, the fastening of screws and hooks, the reconditioning and repair of castings, the rebuilding of shafts, slide bearings, pumps and housings, the renewal of defective threads, the production of templates and models and for repair works on aluminium, light metal and injection moulded parts.

It can be used in machine construction, tool construction, model and mould making, and in many other industrial applications.

Technical Data

| Composition | Epoxy resin mineral-filled |
|--|-----------------------------------|
| Specific Properties | pasty, high temperature resistant |
| Colour after curing | green |
| Mixing ratio by weight resin/hardener | 100:100 |
| Density of the mixture (200g preparation) | 2,0 g/cm ³ |
| Consumption at a coating thickness of 1,0 mm | 2,00 kg/m² |
| Maximium layer thickness for each working step | 15 mm |
| Pot life at +20°C (+68°F) 200g preparation | 30 min. |
| Curing time mechanical loads | 2 h |
| | |

| Final strength after | 3 h |
|--|---------------------|
| Mean strength at +25°C (+77°F) acc. to DIN 532 | 281-83 ASTM D 1002: |
| Pressure | 80 Mpa |
| Pull | 30 Mpa |
| Bending | 56 Mpa |
| E-Modul | 4.000 - 6.000 Mpa |
| Shore D (ATSM D 1706) | 87 |
| Shrinkage | 0,005 % |
| Thermoforming resistance | +95 °C |
| Temperature resistance | -35 to +200 °C |
| ISSA-Code | 75.509.37/38/39 |
| IMPA-Code | 81 29 52/53/54 |

Information about surface pre-treatment and processing can be found in the manual.

Surface pre-treatment

Degrease and clean surface to be treated, roughen if necessary.

Processing

Mix resin and hardener in a ratio of 1:1 and knead thoroughly until mixture has turned into a uniform green. Then apply mastic onto the cleaned surface. On larger gaps, wire screen or glass fibre cloth tape may be recommended to bridge the gap. The hardened material can be machined (drilled, filed, tapped) and painted without any pre-treatment.

Storage

When kept at a constant room temperature of about +20°C and unopened in dry conditions, WEICON Epoxy Resin Putty will keep for at least 24 months. Avoid direct sunlight.

Safety and health

When using WEICON products, the physical, safety technical, toxicological and ecological data and regulations in our EC safety data sheets (www.weicon.com) must be observed.

Available sizes:

| 10500100 | Epoxy Resin Putty 100 g |
|----------|-------------------------|
| 10500400 | Epoxy Resin Putty 400 g |
| 10500800 | Epoxy Resin Putty 800 g |

Accessories:

| 10604025 | Mould Release Agent Liquid F 1000, 250 ml |
|----------|---|
| 10604515 | Mould Release Agent Wax P 500, 150 g |
| 10850005 | Glass Fibre Cloth Tape, 50 mm |
| 11202400 | Sealant and Adhesive Remover, 400 ml |

11207400 Surface Cleaner, 400 ml

Note

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequated boratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

WEICON GmbH & Co. KG (Headquarters) Germany phone +49 (0) 251 9322 0 info@weicon de

WEICON SA (Pty) Ltd South Africa phone +27 (0) 21 709 0088 info@weicon.co.za WEICON Middle East L.L.C. United Arab Emirates phone +971 4 880 25 05

WEICON South East Asia Pte Ltd Singapore phone (+65) 6710 7671 WEICON Inc.
Canada
phone +1 877 620 8889
info@weicon.ca

WEICON Czech Republic s.r.o. Czech Republic phone +42 (0) 417 533 013 WEICON Kimya Sanayi Tic. Ltd. Şti. Turkey phone +90 (0) 212 465 33 65 info@weicon.com.tr www.weicon.com.tr

WEICON Ibérica S.L. Spain phone +34 (0) 914 7997 34 info@weicon es WEICON Romania SRL Romania phone +40 (0) 3 65 730 763 office@weicon.com